


Tecodirekt Tecodirect	0.5%	2%	C.I. Direct	Xenonlicht Xenon lamp 1/12 RTT/SD 1/1 RTT/SD	SDC	HT Eignung HT suitability	Wäsche Washing 40 °C			Schweiss Perspiration alk./alk.			Schweiss Perspiration sauer/acid			
							N	CO	WO	N	CO	WO	N	CO	WO	
Gelb 4GL 150% Yellow 4GL 150%			Y 44	4 4-5	A	-	3	2	4-5	4	2	5	4	2	5	o.N./w.a.
							3-4	2-3	5	4-5	3	5	4-5	3	5	m.N./a
Gelb L Yellow L			Y 86	4-5 6	B	(+)	3-4	2-3	4	3-4	3	4-5	3-4	3	4-5	o.N./w.a.
							4-5	3	4-5	4-5	4-5	5	4-5	4-5	5	m.N./a
Orange 2GL Orange 2GL			O 39	4-5 5-6	B	+	3-4	2	5	4	2	4-5	4-5	2-3	4	o.N./w.a.
							4-5	3	5	5	4-5	5	4-5	4-5	5	m.N./a
Orange 7GL Orange 7GL			O 46	4-5 6-7	B	+	3-4	2-3	4-5	4	2	3-4	4	2	3	o.N./w.a.
							4	3-4	5	4-5	5	5	4-5	5	5	m.N./a
Scharlach BNL 200% Scarlet BNL 200%			R 89	3-4 4-5	B	+	4	3	4-5	4-5	3	4-5	4	3	4-5	o.N./w.a.
							4-5	3-4	5	5	4-5	5	5	5	5	m.N./a
Rot 4G Red 4G			R 23	3 3-4	C	(+)	3-4	2	5	4	2-3	4-5	4	2-3	4-5	o.N./w.a.
							4	3	5	4-5	4	5	4-5	4-5	5	m.N./a
Rot 3BL 200% Red 3BL 200%			R 80	3-4 4	B	-	4	3	4-5	3	2	4	3	2	3-4	o.N./w.a.
							4-5	3-4	5	4-5	4-5	5	4-5	4-5	4-5	m.N./a

o.N./w.a. = ohne Nachbehandlung / without aftertreatment
m.N./a = mit kationischer Nachbehandlung / with cationic aftertreatment

Tecodirekt Tecodirect	0.5%	2%	C.I. Direct	Xenonlicht Xenon lamp 1/12 RTT/SD 1/1 RTT/SD	SDC	HT Eignung HT suitability	Wäsche Washing 40 °C			Schweiss Perspiration alk./alk.			Schweiss Perspiration sauer/acid			
							N	CO	WO	N	CO	WO	N	CO	WO	
Rot 6BL 200% Red 6BL 200%			R 79	4-5 6	B	-	3-4	2-3	4-5	4	2-3	4	4	2	4	o.N./w.a.
							4-5	4-5	5	4-5	4	4-5	4	4	4-5	m.N./a
Rubin 3BL 300% Rubine 3BL 300%			R 83	5 6-7	B	(+)	3-4	2	4	3	2-3	3-4	3	2-3	4	o.N./w.a.
							4-5	3-4	4-5	5	4-5	5	5	4-5	4-5	m.N./a
Blau BL 200% Blue BL 200%			B 71	4 5-6	B	+	3-4	3-4	4-5	3-4	2-3	4-5	4	3	4-5	o.N./w.a.
							4-5	4	4-5	4-5	4-5	5	4-5	4	5	m.N./a
Blau 2GL 150% Blue 2GL 150%			B 106	5 6-7	B	+	2	2-3	4-5	3	1-2	3	3	1	2	o.N./w.a.
							4	3	5	4-5	4-5	5	5	4-5	5	m.N./a
Türkis FBL Turquoise FBL			B 199	5 6	B	+	3	3-4	5	2-3	1	2	2-3	1-2	2	o.N./w.a.
							4-5	4-5	5	4-5	4-5	4-5	5	4-5	5	m.N./a
Grün BL Green BL			Gr 26	3-4 5	B	+	4	3-4	4-5	4-5	2	4-5	4	2-3	4-5	o.N./w.a.
							4-5	4	4-5	5	5	5	5	4-5	5	m.N./a
Braun BL Brown BL			Br 103	4 5	B	+	3-4	2-3	5	4	3	4-5	4	3	4-5	o.N./w.a.
							4-5	4	5	5	4-5	5	5	4-5	5	m.N./a

o.N./w.a. = ohne Nachbehandlung / without aftertreatment
m.N./a = mit kationischer Nachbehandlung / with cationic aftertreatment

Tecodirekt Tecodirect	0.5%	2%	C.I. Direct	Xenonlicht Xenon lamp 1/12 RTT/SD 1/1 RTT/SD	SDC	HT Eignung HT suitability	Wäsche Washing 40 °C			Schweiss Perspiration alk./alk.			Schweiss Perspiration sauer/acid			
							N	CO	WO	N	CO	WO	N	CO	WO	
							Braun 2GL Brown 2GL			Br 115	4 5	B	-	4 4-5	2-3 3-4	
Grau GL 250% Grey GL 250%			Blk 112	4 6	B	+	2-3 4	2-3 3-4	4-5 5	2-3 4-5	2-3 4	4 4-5	3 4-5	2-3 4	4 4-5	o.N./w.a. m.N./a

Tecodirekt Tecodirect	2%	4%	C.I. Direct	Xenonlicht Xenon lamp 1/12 RTT/SD 1/1 RTT/SD	SDC	HT Eignung HT suitability	Wäsche Washing 40 °C			Schweiss Perspiration alk./alk.			Schweiss Perspiration sauer/acid			
							N	CO	WO	N	CO	WO	N	CO	WO	
							Marineblau FGL 200% Navy FGL 200%			B 85	4 6	A	+	3 4-5	2-3 4-5	
Schwarz UR 600% Black UR 600%			Blk 22	- 4	B	(+)	3-4 4-5	2-3 3-4	4 5	4-5 4-5	3 4-5	4 4-5	4-5 5	3 4-5	4 4-5	o.N./w.a. m.N./a
Schwarz B Black B			Blk 80	- 4	B	+	4 4-5	1-2 3	4-5 5	4-5 4-5	2-3 4	4-5 4-5	4-5 4-5	2-3 4	4-5 4-5	o.N./w.a. m.N./a

o.N./w.a. = ohne Nachbehandlung / without aftertreatment
m.N./a = mit kationischer Nachbehandlung / with cationic aftertreatment

